

Garage Force System Mil Thickness

System	Product	Coverage	Units	Nominal DFT of System
FULL CHIP BROADCAST	Base Coat	350	SF/Gallon	4.5 mils
	1/4" Chip	10	LB/SF	5 mils
	Top Coat	175	SF/Gallon	7.3 mils
<i>DFT=Dry Film Thickness</i>				Total DFT: 16.8 mils
QUARTZ DOUBLE BROADCAST	Base Coat	350	SF/Gallon	4.5 mils
	Quartz	2	LB/SF	16 mils
	Top Coat	125	SF/Gallon	10.25 mils
	Quartz	2	LB/SF	16 mils
	Top Coat	125	SF/Gallon	10.25 mils
<i>DFT=Dry Film Thickness</i>				Total DFT: 57 mils
FULL CHIP DOUBLE BROADCAST	Base Coat	350	SF/Gallon	4.5 mils
	1/4" Chip	10	LB/SF	5 mils
	Top Coat	175	SF/Gallon	7.3 mils
	1/4" Chip	10	LB/SF	5 mils
	Top Coat	175	SF/Gallon	7.3 mils
<i>DFT=Dry Film Thickness</i>				Total DFT: 29.1 mils
MEDICI	Base Coat	350	SF/Gallon	4.5 mils
	Cyclo1 Tinted	500	SF/Gallon	3 mils
	Cyclo1/Additive	500	SF/Gallon	3 mils
	Abrasion Resistance Additive	1	Bag/Gal. Cyclo1	2.9 mils
<i>DFT=Dry Film Thickness</i>				Total DFT: 13.4 mils
METALLIC	Base Coat	350	SF/Gallon	4.5 mils
	Self Leveling Epoxy Clear	50	SF/Gallon	32 mils
	Cyclo1/Additive	500	SF/Gallon	3 mils
	Abrasion Resistance Additive	1	Bag/Gal. Cyclo1	2.9 mils
<i>DFT=Dry Film Thickness</i>				Total DFT: 42.4 mils
SOLID COLOR 3 COAT SYSTEM	Base Coat	350	SF/Gallon	4.5 mils
	Cyclo1 Tinted	500	SF/Gallon	3 mils
	Cyclo1/Additive	500	SF/Gallon	3 mils
	Abrasion Resistance Additive	1	Bag/Gal. Cyclo1	2.9 mils
<i>DFT=Dry Film Thickness</i>				Total DFT: 13.4 mils
GRIND AND SEAL 3 COAT SYSTEM	Cyclo1	400	SF/Gallon	3.6 mils
	Cyclo1	500	SF/Gallon	3 mils
	Cyclo1/Additive	500	SF/Gallon	3 mils
	Abrasion Resistance Additive	1	Bag/Gal. Cyclo1	2.9 mils
<i>DFT=Dry Film Thickness</i>				Total DFT: 12.5 mils

**Mil Thickness measurements are for reference. **

**Mil Thickness will vary by the actual spread rate achieved by the applicator installing the coating system. **